

PRODUCT DESCRIPTION The fastest tank lining coating in the industry.

INTENDED USES A marine grade **potable water certified** epoxy tank coating for new builds when used as a single coating which can also be used in ballast tanks, void spaces, cofferdams and wet spaces. For use in maintenance and repair when used with Easy Prime.

PRODUCT INFORMATION	Part A (Color)	421-Beige							
	Finish/Sheen	Gloss							
	Part B (Curing Agent)	222							
	Volume Solids	100% (Wet mils = Dry mils) (ISO 3233:1998)							
	RAL 7035	1.3 +/- 0.1							
	Mix Ratio	2 volume(s) Part A to 1 volume(s) Part B							
	Film Thickness	New Build: 12 Wet Mils (300 microns wet). Maintenance: 9 Wet Mils (225 microns wet).							
	Theoretical Coverage	3.29 m²/litre (134 Ft²/Gall) at 12 Mils , add 20% for overspray loss. 4.37 m²/litre (178 Ft²/Gall) at 9 Mils , add 20% for overspray loss. Airless Spray, Brush, Roller							
	Method of Application	Part A >100°C; Part B >100°C; Mixed >100°C							
	Flash Point (Typical)								
Drying Information		10°C		15°C		25°C		35°C	
	Touch Dry [ISO	24 hrs		12 hrs		8 hrs		5 hrs	
	9117/3:2010] Hard Dry [ISO	36 hrs		24 hrs		18 hrs		8 hrs	
	9117-1:2009] Pot Life	no data		90 mins		60 mins		45 mins	
Overcoat		Substrate Temperature							
		10°C		15°C		25°C		35°C	
		Min	Max	Min	Max	Min	Max	Min	Max
		36 hrs	unlimited	24 hrs	unlimited	18 hrs	unlimited	10 hrs	unlimited

POTABLE WATER IN SERVICE INSTRUCTIONS

Drying Information	10°C	15°C	25°C	35°C
Curing Duration	no data	60 hrs	36 hrs	36 hrs

Once the curing duration is complete, flush fresh water tank once prior to use.

CERTIFICATIONS

All Certification are NSF ANSI Standard 61 unless otherwise noted

- Potable Water - Carriage of Potable Water
- Potable Water - Certification for tanks greater than or equal to 200 gallons
- Potable Water - Certification for pipe diameter greater than or equal to 24"
- Potable Water - Certification for pipe fitting diameter greater than or equal to 2"
- Potable Water - Certification for surface area to volume ratio not to exceed 67.7 cm²/L
- Seawater Ballast Tanks - Maintenance survey (Lloyd's Register)
- Certificate of Design Assessment - Ballast tank repair (American Bureau of Shipping)

SURFACE PREPARATIONS

Simply stated the steel surface must be:

Clean: No staining to white rag when rubbed across steel surface

Dry: No visible moisture on the steel surface

Tight: No loose material when a wire brush is pulled across the surface of the metal

For new build sweep blast entire tank to Sa1.0. For maintenance and repair refer to Easy

Prime surface preparation. A surface profile of 50 - 100 microns is required.

Weld Seams and sharp edges must be stripe coated with Easy Flex

APPLICATION

MIXING

Material is supplied in a Uni-Pak container. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.

(1) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.

THINNER

Not recommended.

AIRLESS SPRAY

Recommended

Tip Range 0.53-0.58 mm (21-23 thou)

Total output fluid pressure at spray tip not less than 211 kg/cm² (3000 p.s.i.)

Mixed material temperatures should be between 30-35°C (86 - 95F) for optimum spraying.

CONVENTIONAL SPRAY

Application by conventional spray is not recommended.

BRUSH

Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.

ROLLER

Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.

CLEANER

Methyl Ethyl Ketone (CAS # 78-93-3)

PERFORMANCE

Adhesion Pull Test	ASTM D4541	76.7 KG/cm ² (1,090 psi)
Elongation	ASTM D2794	3.05 Joules (27-inch pounds)
Conical Mandrel Bend	ASTM D522	>34%
Weight Gain (30-day immersion)	ASTM D471	>0.5% Diesel Crude
		>0.5% Oil
Heat Resistance Continuous	ASTM D2485	150C (302F)
90 Day Salt Water Immersion (50C)		No Effect

WORK STOP / CLEANUP

Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with Cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed material.

Clean all equipment immediately after use with cleaner. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

WELDING

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

PACKAGING SIZE

10 Liter UniPak Pail (2.64 Gall) Mixed , 30 IBS Gross Weight

UN SHIPPING

Non-hazardous , non-regulated

SHELF LIFE

36 Months

LIMITATIONS

At ambient temperatures below 25°C paint lines must be lagged. In-line heaters should not be used unless absolutely necessary. For maximum performance the curing temperature should be kept below 35°C. Particular care should be taken to avoid exceeding this in localized areas when artificial heating is introduced. The climatic conditions within the tank must be controlled to maintain a maximum relative humidity of 90%. The drying times and overcoating intervals may alter due to various on-site factors such as tank configuration and ventilation rates.

IMPORTANT NOTE

The information contained in this data sheet is to the best of our knowledge true and accurate; but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. Each user should review these recommendations in the specific context of the intended use and determine whether they are appropriate. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose.

www.royalcoatings.net