

Royal PC-12

ASPHALTIC PAINT

◆ SINGLE COMPONENT

◆ WATERBORNE SAFE

◆ PASSES LEACH TEST

◆ UL ANSI / NSF 61 & 372 , AWWA C104/A21 Certified

◆ VERY FAST DRY WITH ZERO VOC AND ZERO HAPS

◆ YEARS OF RELIABLE SERVICE



DRINKING WATER SYSTEM COMPONENTS
ANSI/NSF 61
5N16, 6N21

Royal PC-12 was designed to replace traditional cutback asphaltic coatings especially where VOC and safety considerations are very important. Royal PC-12 is virtually odorless and contains no VOCs or HAPs. It is designed to be spray applied at 5 mils WFT or dipped and cures to 3 mils DFT. It has excellent gloss and dries non tacky extremely fast. Forced ventilation will speed the cure of the film.

TECHNICAL DATA

Solids	57-63%
VOCs	0
Finish	Semigloss - nontacky
Odor	None
Flash Point	None
HAPS	0
Minimum dry time for Potable Water	7 Days

Safety:

*Always refer to Royal's MSDS before the use of any of our products.

Packaging: Packaging is available in bulk, totes, and drums

Storage:

When purchased in bulk the product must be maintained in a temperature range of 80°F to 130°F. In addition the product must be agitated for 10 minutes each day. Failure to follow these instructions can cause at least a soft settling of the product. Do not add more water to the product being stored. For best results on corrosion we recommend not to add any water. For PC-12 sold in a drum it is only necessary to store above 50°F. This product is delivered in a more viscous solution to help prevent settling. Mechanically agitate the drum prior to use. For further assistance and information contact:

Manufactured by:

Royal Coatings, Inc.
2705 Concord Road
Belle Chasse, LA 70037
Phone: 504-392-8811
Email: info@royalcoatings.net

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. ROYAL COATINGS INC.. disclaim any liability incurred in connection with the use of this data or suggestions

03/15/2021