



10366 Roselle St. Suite C • San Diego, CA 92121 • 858-535-9979

## Analytical Testing Report

Mark Parker  
Royal Coatings Inc.  
2705 Concord Road,  
Belle Chase, LA 70037

11-24-21

ECA #21313

The analysis of the material (s) has been completed and the results are given on the next page.  
The sample information is:

---

Customer Identification: **1. PC-12/ Lot BC211012-PC-12/ 10-12-21**

ECA Sample #: 1. 21313a

Date Received: 10-14-21

Test Requested: EPA Method 24

Client: **Royal Coatings Inc.**

If there are any questions, please give me a call @ (858) 535-9979. We appreciate your business!

Sincerely,

Jim Polansky, M.S., M.A.

Scientist

Quality Control Officer



10366 Roselle St. Suite C • San Diego, CA 92121 • 858-535-9979

## Results/ Method 24

PC-12/ Lot BC211012-PC-12/ 10-12-21

Density (g/L)	Total Volatiles (- exempt VOCs) (%w/w)	Water Present (% w/w)	VOC (Coating) (g/L)	VOC (material) (g/L)
Test#1: 1.03g/mL	44.6%	43.8%		
Test #2: 1.03g/mL	44.4 %	43.8%		
Test #3:	44.5%			
<b>Average: 1.03 g/mL</b>	<b>44.5%</b>	<b>43.8%</b>	<b>13 g/L</b>	<b>7 g/L</b>